

FANTASTICOT Nm 23.000

- **Composizione:** 53%CO/Cotone 27%PL-PBT/Poliestere 20%PA/Poliammide

- **Impiego e consigli:** 1 capo rett.fin.12

- **Tintura / cotte ottimali :** Tinto matassa – tutti colori stock service

- **Solidità colori:** lavaggio 3/4 luce 4 secco 4

Per i colori di particolare intensità e brillantezza le solidità possono variare.

Attenzione specifiche : Questo filato detiene una moderata elasticità, che conferisce al manufatto un effetto elasticizzato-comfort, questo si ottiene con abbondante vapore sui teli dopo la smacchiatura ed un successivo lavaggio delicato in acqua tiepida con sapone neutro. Asciugare a velocità ridotta avendo cura di non essiccare troppo i capi. Il rientro varia a seconda dei punti maglia e della loro fittezza, pertanto raccomandiamo prima di procedere al confezionamento dei capi stessi, di effettuare prove atte a garantire le misure delle taglie al consumatore finale.

Dopo la fase di lavaggio i capi potrebbero subire un leggero assestamento dimensionale, pertanto consigliamo di effettuare le dovute prove, prima di procedere alla completa tessitura dei capi. Vista la caratteristica del filato, si consiglia di tessere a velocità moderata prestando attenzione alla realizzazione del manufatto. Questo filato è stato ottenuto con metodi artigianali, pertanto, eventuali leggere disomogeneità di colore ed effetto sono da considerarsi caratteristiche e non difetti del prodotto. Questo articolo ci impone un numero minimo di nodi al kilogrammo, pertanto consigliamo all'utilizzatore di prendere conoscenza affinché il filato possa essere ammagliato nel modo più corretto.

- **Istruzioni di lavaggio:** Per mantenere un buon livello di pilling ed una mano morbida e gonfia, si consiglia di lavare i capi sul rovescio con acqua a 30 °C ed ammorbidente siliconico. Lasciare per 4-5 minuti fermi in ammollo. Poi circa 15 minuti suddivisi in delicata azione meccanica e scarico finale con centrifuga. Asciugatura in tumbler con azione moderata a 50-60 °C per circa 15/20 minuti. Nei filati con alta percentuale di mohair o alpaca, si consiglia di effettuare un prelavaggio a 30 °C con saponi neutri per sgrassare le fibre.

In caso di maglieria rigata o jacquard con tinte forti e contrastanti, consigliamo di lavare il capo solo a secco.

- **Nobilizzazione ed istruzioni per la manutenzione dei capi:** Per ottenere una buona mano e la giusta stabilità dimensionale del manufatto è sufficiente un abbondante vaporizzo durante lo stiro, evitando l'uso del piano superiore affinché il tessuto non subisca schiacciamenti o chiazze indesiderate, oppure lavare a secco con i normali solventi che si trovano in commercio. Per il trattamento con acqua, suggeriamo di lavare delicatamente in acqua con sapone ed ammorbidente neutro, avendo cura di girare sul rovescio i capi prima di tale operazione. Si consiglia di asciugare a velocità ridotta avendo cura di non essiccare troppo i capi.

- **Percentuale di scarto lavorazione:** Considerare una percentuale del 5-6%. Non si accettano reclami o resi per un quantitativo di filato smacchinato superiore a 5 Kg per bagno.

- **Attenzione specifiche:** Il manufatto deve essere lavorato a due o più guidafile. Per mancata osservanza di queste istruzioni, non sarà preso in considerazione nessun tipo di reclamo.

Il Filato rispetta tutti i parametri del regolamento REACH

- **Composition:** 53%CO/Cotton 27%PL-PBT/Polyester 20%PA/Polyamide

- **Knitting Suggestion:** 1 end flat machine g.12

- **Dyeing process/ Optimal dyelots :** Hanks-dyed – all colour stock service

- **Colour fastness:** washing 3/4 light 4 dry 4

For especially brilliant and intense colours, colour fastness may vary.

This yarn has a little stretching features, which can be increased with an abundant steaming on the finished swatches, avoiding the iron, and a further washing in lukewarm water with soap and neutral softener.

Rinse and dry at a reduced speed taking care not to over-dry the garments, shrinkage level varies according to the pattern to be created.

Before producing the garments, the necessary tests must be effected thus guaranteeing the sizes to the consumer.

After washing treatment, garments could have a dimensional change. Therefore we suggest to make trials before proceeding with knitting. We suggest to set machine at low speed and do not use stitches which can damage the yarn. This yarn has been achieved through craftsman proceedings, therefore any possible slight shade differences must not be considered as defects but distinctive features of the product. A minimum number of knots per kilogram has to be considered due to the constructions, the producer must take note of this in order to knit the yarn in the most appropriate way.

- **Washing Instruction (Method applied on our collection' swatches):** To keep a good pilling rate and a soft handfeel, we suggest to wash garments on the back side with water at 30 °C and siliconic softener. Keep them in the water for 4-5 minutes. Then around 15 minutes divided in a delicate mechanical action and final draining with centrifuge. Drying in tumbler (very light mechanical action) for 15-20 minutes at 50/60 °C. We suggest to apply a pre-washing at 30 °C with neutral soaps to these articles with high percentage of alpaca and mohair, in order to degrease the fibers. In case of striping or jacquard knitwear with strong and contrasting colours, we suggest only to dry clean wash.

- **Ennobling:** In order to obtain a soft hand and a correct product dimensional stability it is advisable, to steam strongly when ironing, avoiding the use of iron, so that the yarn does not get squashed nor make glossier "spots". Dry cleaning with the normal solvents in commerce, or delicately to wash it in lukewarm water, with soap and neutral softener, taking care to perform these processes on reverse side of the knitwear.

- **Wastage percentage:** We recommend to calculate a 5-6%. We do not accept claims or returns for quantities of knitted yarn higher the 5 Kg per lot.

- **Warnings :** Yarn must be knitted with 2 or more yarn-carriers (one carrier for each course/row of knitting). Pinori Filati SpA will not be responsible for any claim due to non-compliance of this instruction.

The yarn respect all the parameters of the rule REACH

Percentuale media di condizionatura/Conditioning rate: 2,00/2,50%

Tariffa doganale / Custom Code : 52064200

Peso al metro quadro /Weight per square meter : 230 gr/mq – 230 gsm

Simboli di manutenzione/Washing symbols :



simboli lavaggio per colori uniti/care instruction for solid colours