



BRIDGE NM 3000

- **Composizione:** 17% WM/Kid Mohair 21% WO/Lana Merino Irrestringibile 17% VI/Viscosa 45% PA/Poliammide
- **Impiego e consigli:** 1 capo rett.fin.3-5
- **Tintura e cotte ottimali (colori pretinti) :** Tinto tops - minimo quantitativo 30 Kg con supplementi fino a 65 Kg
- **Tintura-bagni ottimali (colori-tinti) :** in matassa – bagni ottimali in kgs :15*-35*-70*-140-280-560,con supplementi fino a 63 kg.
- **Solidità colori:** lavaggio 3/4 luce 4 secco 4
Per i colori di particolare intensità e brillantezza le solidità possono variare.
- **Attenzioni specifiche:** In caso di riparaffinatura del filato, consigliamo di regolare le roccatrici a bassa velocità, per ottenere rocche morbide con densità uniforme.
L'effetto coloristico di questo articolo è stato ottenuto con metodi artigianali, pertanto piccole differenze di tonalità possono presentarsi sui capi in maniera casuale e questo è da considerarsi caratteristica e non difetto del prodotto.
In questo articolo ci sono colori tinti e pretinti ,quindi si consiglia di effettuare le dovute prove di resa nei teli prima di effettuare la produzione
- **Istruzioni di lavaggio:** Per mantenere un buon livello di pilling ed una mano morbida e gonfia, si consiglia di lavare i capi sul rovescio con acqua a 30 °C ed ammorbidente silconico. Lasciare per 4-5 minuti fermi in ammollo. Poi circa 15 minuti suddivisi in delicata azione meccanica e scarico finale con centrifuga. Asciugatura in tumbler con azione moderata a 50-60 °C per circa 15/20 minuti. Nei filati con alta percentuale di mohair o alpaca, si consiglia di effettuare un prelavaggio a 30 °C con saponi neutri per sgrassare le fibre.
In caso di maglieria rigata o jacquard con tinte forti e contrastanti, consigliamo di lavare il capo solo a secco.
- **Nobilitazione ed istruzioni per la manutenzione dei capi: Dopo la fase di lavaggio, i capi potrebbero subire un leggero assestamento dimensionale, ed un normale rientro, pertanto consigliamo di effettuare le dovute prove, prima di procedere alla completa tessitura dei capi.**
Per ottenere una buona mano e la giusta stabilità dimensionale del manufatto è sufficiente un abbondante vaporizzo durante lo stiro, evitando l'uso del piano superiore affinché il tessuto non subisca schiacciamenti o chiazze indesiderate, oppure lavare a secco con i normali solventi che si trovano in commercio. Per il trattamento con acqua, suggeriamo di lavare delicatamente in acqua con sapone ed ammorbidente neutro, avendo cura di girare sul rovescio i capi prima di tale operazione. Si consiglia di asciugare a velocità ridotta avendo cura di non essiccare troppo i capi.
- **Percentuale di scarto lavorazione:** Considerare una percentuale del 4-5%. Non si accettano reclami o resi per un quantitativo di filato smacchinato superiore a 5 Kg per bagno.
- **Attenzioni particolari: Si consiglia una fase di prestiro ai pannelli prima del lavaggio. Il manufatto deve essere lavorato a due o più guidafili. Per mancata osservanza di queste istruzioni, non sarà preso in considerazione nessun tipo di reclamo.**

Il Filato rispetta tutti i parametri del regolamento REACH

-
- **Composition:** 17% WM/Kid Mohair 21% WO/Merinos Wool Anti-Shrinkage 17% VI/Viscose 45% PA/Polyamide
 - **Knitting Suggestion:** 1 end flat machine g.3-5

- **Dyeing process- Optimal dyelots (tops-dyed):** Tops dyed – minimum 30 Kg with surcharges until 60 Kg
- **Dyeing process-Optimal dyelots (dyed colors) :** hanks dyed - optimum dyelots in kgs : 12*-32*-63*-126-252-505, with surcharges until 63 kilos.
- **Colour fastness:** washing 3/4 light 4 dry 4
For especially brilliant and intense colours, colour fastness may vary.
- **Warnings:** In the event of re-waxing the yarn, set the winders at a low speed, thus attaining soft and uniformly dense cones.

The shades of this yarn have been realised with craftsman proceedings, therefore any possible slight difference of colour-shades must not be considered as defects but distinctive features of the product.

In this yarn we have dyed and top dyed colors so we suggest to make tests, in order to check the different outcome before proceeding with production.

- **Washing Instruction (Method applied on our collection' swatches):** To keep a good pilling rate and a soft handfeel, we suggest to wash garments on the back side with water at 30 °C and silionic softener. Keep them in the water for 4-5 minutes. Then around 15 minutes divided in a delicate mechanical action and final draining with centrifuge. Drying in tumbler (very light mechanical action) for 15-20 minutes at 50/60 °C. We suggest to apply a pre-washing at 30 °C with neutral soaps to these articles with high percentage of alpaca and mohair, in order to degrease the fibers. In case of striping or jacquard knitwear with strong and contrasting colours, we suggest only to dry clean wash.

- **Ennobling: After washing process, the garment could have a slight dimensional adjustment and a light shrinkage, for this reason we suggest to make some tests before proceeding with complete weaving of the garments.**

In order to obtain a soft hand and a correct product dimensional stability it is advisable, to steam strongly when ironing, avoiding the use of iron, so that the yarn does not get squashed nor make glossier “spots”. Dry cleaning with the normal solvents in commerce, or delicately to wash it in lukewarm water, with soap and neutral softener, taking care to perform these processes on reverse side of the knitwear.

- **Wastage percentage:** We recommend to calculate a 4-5%. We do not accept claims or returns for quantities of knitted yarn higher the 5 Kg per lot.
- **Special instruction: We Suggest to pre-iron the panels before washing.**
We recommend strictly to use more than one yarn-carrier when knitting this yarn (one carrier for each course/row of knitting). Pinori Filati SpA, will not be responsible for any claim due to non-compliance of this instruction.

The yarn respect all the parameters of the rule REACH

Percentuale media di condizionatura/Conditioning rate: 3,50/4,00%

Tariffa doganale / Custom Code : 55099100

Peso al metro quadro /Weight per square meter : 240 gr/mq – 240 gsm

Simboli di manutenzione/Washing symbols :



simboli lavaggio per colori uniti/care instruction for solid colours